




## HARDOX TUBE 500



## HARDOX TUBE 500

### General Product Description

Abrasion-resistant tubes for extreme performance and extended service life

Hardox® Tube 500, as hard and tough as our wear plates, offer outstanding performance when you need both high wear resistance and a lighter product.

Despite its hardness, Hardox Tube 500 can be weld, cut, milled and drilled using standard workshop practices. It can replace costly wear products like hard-faced overlay plates and high chrome white iron.

#### Available dimensions

Total Thickness Range: 2- 6 mm

Max Length: 10000 mm

Total Diameter Range: Circular 76- 133 mm

### Mechanical Properties

Wall Thickness (mm)	Hardness <sup>1)</sup> (HBW)
2.0- 6.0	470- 530

<sup>1)</sup> Brinell hardness test, HBW, according to EN ISO 6506-1.

#### Circular

Diameter	3.0mm	4.0mm	5.0mm	6.0mm
76.1 mm	x	x	x	x
88.9 mm	x	x	x	x
101.6 mm	x	x	x	x
108 mm	x	x	x	x
114.3 mm	x	x	x	x
133 mm	x	x	x	x

# HARDOX TUBE 500

## Chemical Composition

C (max %)	Si (max %)	Mn (max %)	P (max %)	S (max %)	Cr (max %)	Ni (max %)	Mo (max %)	B (max %)
0.30	0.70	1.60	0.020	0.010	1.50	1.5	0.60	0.005

The steel is grain refined.

## Carbon Equivalent Values

Wall Thickness (mm)	2.5 - 6 mm
CET	0.41
CEV	0.62

$$CET = C + \frac{Mn + Mo}{10} + \frac{Cr + Cu}{20} + \frac{Ni}{40}$$

## Tolerances

Characteristic	Circular wear tube Tolerances based on the requirements of EN 10210
Outside diameter (D) <sup>1)</sup>	±1%, with a minimum of ±0.5 mm and a maximum of ±10 mm
Out-of-roundness	2%, when D/T ≤ 100
Thickness (T)	±10% when T ≤ 5 mm and ±0.5 mm when T > 5 mm
Straightness	0.20% of total length and 3 mm over any 1 m length
Mass per unit length	Individual tube: ±6%
Standard length	≥ 6000 mm: 0/+50 mm
Exact length	Agreed at the time of enquiry and order

<sup>1)</sup> All external dimensions are measured with a minimum distance from the end of the section. The distance must be a minimum of 100 mm.

## Delivery Conditions

The delivery condition is Q (Quenched).

The Hardox Tube 500 is delivered in as-rolled condition lightly oiled.

Delivery requirements can be found in SSAB's brochure 41-General product information Strenx, Hardox, ArmoX and Toolox-UK or at [www.ssab.com](http://www.ssab.com).

## Fabrication and Other Recommendations

Recommendations can be found in SSAB's brochures at [www.hardox.com](http://www.hardox.com) or consult Tech Support, [help@ssab.com](mailto:help@ssab.com).

Hardox Tube 500 has obtained its mechanical properties by quenching and after roll forming and plasma welding. The properties of the delivery condition cannot be retained after exposure to service or preheating temperatures in excess of 250°C. Hardox Tube 500 is not intended for further heat treatment.

Appropriate health and safety precautions must be taken when welding, cutting, grinding or otherwise working on this product.

Grinding, especially of primer coated plates, may produce dust with a high particle concentration.

# HARDOX TUBE 500



The UK English version of this document shall prevail in case of discrepancy. Download the latest version of this document at [www.ssab.com](http://www.ssab.com)  
Hardox, Strenx, Docol, Dogal, Domex, Toolox, Laser, Armox, Ramor, GreenCoat are trademarks of SSAB Technology AB, Sweden

[www.ssab.com](http://www.ssab.com)

DATA SHEET 834 HARDOX TUBE 500 2013-03-19

**SSAB**